

Acrylic acid base swelling thickener

ASE-60

Features and advantages:

 Ase-60 is a non-associating anionic base swelling thickener.
 It is a crosslinked polyacrylic acid emulsion containing acidic groups.

2. Ase-60 has no association structure in its molecules and is insensitive to emulsions and emulsifiers. It has strong versatility in various formulations. Ase-60 can effectively improve the low shear viscosity and make the coating have high pseudoplasticity. It can be used as main thickener or co-thickener to obtain excellent water resistance.

3. The coating with ASE-60 as the main thickener has a higher yield value and produces gel structure, which is suitable for preparing three-dimensional pattern effect of wool or relief paint, but the amount of ASE-60 is too large when used alone.

USES:

1, emulsified silicone oil defoaming agent, the recommended amount of 1-3%

2, fabric coating glue, recommended to add 0.5-1%

3, coating printing glue, recommended to add 1-3%

4, pressure sensitive adhesive emulsion, recommended to add
0.5-1%

5, the recommended amount of inner and outer wall latex paint

Tianjin Ruike Chemical Co. LTDTel:+86 18526852692Add:Room 116-11, 160 Xiangyuan Road, Jingjin Science and Technology Valley Industrial Park, Wuqing
District, Tianjintjrkhg@126.comwww.rk-chem.com



is 0.2-0.6%

6, water-based ink, recommended to add 0.5-1%

```
7, water-based coating adhesive, recommended to add 0.2-0.5%
```

Product specifications:

| appearance | Milky liquid |
|-------------------------|-------------------|
| Chemical composition | Acrylic copolymer |
| PH | 3.5 |
| Non-volatile portion of | 28±1% |
| Brinell viscosity | < 50cp (25℃) |

Recommended dosage: add 0.5~2.0% to the total amount of paint (finished product form), the specific dosage should be subject to the experiment;

Usage: before use, adjust PH value of thickening system to 8 ~ 9 with ammonia water, then dilute ASE-60 with water in a ratio of 1:2, and add slowly under low speed stirring.

Packing: 50kg plastic drum/ton drum;

Storage: the product should be sealed and placed in a cool, dry and ventilated place. If it cannot be used all at once, tighten the cover after use to prevent caking or crusting.